

WE #50LAC

CONDUCTIVE ALUMINIUM FOIL TAPE

Properties :

Physical	Std. (IEC,ISO,DIN etc.)	Test Method	Unit	Value (S.I.Metric etc.)
Backing Thickness	ASTM	D3759	mm	0.05
Adhesive Thickness	ASTM	D3759	mm	0.03
Total thickness	ASTM	D3759	mm	0.09
Adhesion to Steel	ASTM	D3759	g/25mm	1150
Elongation at Break	ASTM	D3759	%	17
Tensile Strength	ASTM	D3759	g/25mm	1000
Resistance	ASTM	257	Ohm	<0.05
Shielding Effectiveness			db	80-115

Material Chemical Composition:

Aluminium foil, Conductive acrylic adhesive

Storage Condition / Shelf Life:

Store in a dry location, out of direct sunlight and keep away from all sources of heat. Ideal conditions are 20°C and 50% relative humidity.

To obtain best performance, please use this product within 12 months from the date of manufacture.

Waste Disposal & the Environment:

Reclaim if feasible. If product can't be reclaimed, dispose of waste product in a sanitary landfill. Alternatively, incinerate the waste product in an industrial, commercial incinerator.

For Additional Information:

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on test believed to be reliable.